



## Technical Data

## Method of installation

### Glued

	Divina-Series R	Divina-Series T	Dynamic Cork
Finishing		Finishing	
Water based finishing		Water based homopolymer finishing	

General Properties	Standard-Test Method	Unit	Specification	
			EN 13085 + EN 15102	EN 12781 + EN 15102
Dimensions	EN 427/ EN 426	mm	Width - 700 ± 0,50% Length - 5500 ± 0,50%	600x450 ± 0,50% 600x300 ± 0,50%
		inches	Width - 28-9/16 ± 0,50% Length - 216-9/16 ± 0,50%	23-5/8x17-23/32 ± 0,20% 23-5/8x11-13/16 ± 0,20%
Thickness	ISO 7322	mm	2 ± 0,20	3 ± 0,15
Squareness	EN 427	mm	<0,30	<0,30
Straightness	EN 427	mm	<0,50	<0,50
Apparent Density	EN 672	Kg/m <sup>3</sup>	200-250	≥ 300
Dimensional Stability	EN ISO 23999	%	≤ 0,20	≤ 0,40
Resistance to Traction	ISO 7322	kPa	≥ 300	≥ 300
Water Content	EN 12105	%	≤7	≤5
Curling	EN ISO 23999	mm	≤6	≤6
Safety Properties (EN 15102)	Standard-Test Method	Unit	Specification	Specification
Formaldehyde Emission	EN 12149, method C	mg/kg	<10	<10
Vinyl Chloride Monomer (VCM)	EN 12149, method B	mg/kg	<0,01	<0,01
Migration of heavy metals	EN 12149, method A	mg/kg	< maximum allowed value	< maximum allowed value
Additional Properties	Standard-Test Method	Unit	Specification	Specification
Sound Absorption	ISO 354	aw	0,10	0,10
Thermal Resistance	EN 12667	(m <sup>2</sup> .K)/W	0,0506	0,0571